

SUPER SEAL PLUS

Semi-elastic putty



It is a surface treatment putty that gives elasticity to the coating film by using special acrylic emulsion resin and appropriate pigment. It is excellent in water resistance, alkali resistance, workability and adhesion. In particular, it is a semi-elastic putty of excellent quality with the advantages of exterior putty and elastic putty.

Usage

Sealing agent of commercial buildings/residential buildings/public facilities, etc.

Specification

Paint type	Special acrylic emulsion water-based exterior / Elastomeric putty		
Drying time	Category	20°C	Remarks Based on film thickness 1mm
	Surface-drying	60 minutes	
	Dry-Hard	24 hours	
Thinner	No dilution (tap water if necessary)	Coating Method	Brush, roller, spray coating.
Specific gravity	Approx. 1.58	Solid volume ratio	Approx. 61 %
Theoretical Coverage	0.3~0.4 m ² /kg	Thickness of dried film	1mm
	Theoretical application amount may vary depending on the coating method and film thickness.	Color	White
Re-coating interval	20°C, Sufficient ventilation for a minimum of 24 hours	Top coat	KS M 6010 Class 1 Grade 1/2
Storage and preservation	12 months (Dry, cool, and dark place with good ventilation, room temperature 5°C~30°C, humidity less than 80%)		

Product Properties (Physical Property Data)

Excellent workability	The coating surface is not rough but smooth, thus the film appearance is beautiful and there is almost no uneven brightness on the top coat.
Top coat suitability	As a top coat, it can be used for both grade 1/grade 2.

How to Use

Surface treatment	1. Completely remove dust, dirt, oil, etc. after sufficiently curing the basis material. (more than 30 days for new coating)
Coating Method	1. Apply by scrapping thinly with a putty construction knife and scraper. If a thick application is required, apply thinly many times. 2. Apply a wet film thickness of 2 mm or below at one time and proceed with the subsequent coating after drying.