

# SOON&SOO 100

## Water-based interior paint



Soon&Soo interior paint is an eco-friendly type of water-based paint containing very low levels of volatile organic compounds and heavy metals in addition to having little odor in painting and drying processes. It is also an interior vinyl paint made mainly of vinyl emulsion, having excellent hiding power, smoothness and workability. It is an economical interior water-based paint that makes the appearance smoother and cleaner after painting than general water-based paints.

### Usage

Finish coating for indoor ceilings and walls of alkaline material such as concrete, cement mortar, plasterboard, etc.

### Specification

Paint type	Emulsion water-based interior / Top coat			
Drying time	Category	10℃	20℃	30℃
	Dry-hard	2 hours	1 hour	40 minutes
	Time required for re-coating (min.)	6 hours	3 hours	2 hours
Thinner	Tap water(dilution rate: up to 20%, volume ratio)		Coating Method	Brush, roller, spray coating
Specific gravity	Approx. 1.43		Solid volume ratio	Approx. 33%(based on white color)
Theoretical Coverage	5~7m <sup>2</sup> /ℓ/2times		Thickness of dried film	60μm (2coats recommended)
Re-coating interval	20℃, sufficient ventilation for a minimum of 3 hours		Color	White
Gloss	Matte			
Storage and preservation	12 months (Dry, cool, and dark place with good ventilation, room temperature 5℃~30℃, humidity less than 80%)			

### Product Properties (Physical Property Data)

Price competitiveness	It is a product with excellent economic feasibility at a reasonable price.
Eco-friendly properties	It is a LOW VOC, little odor during painting and drying. Environmental mark certified.

### How to Use

Surface treatment	<ol style="list-style-type: none"><li>1. The material should be sufficiently cured (cured more than 30 days at 20℃)</li><li>2. Laitance, dust, oil and other contaminants on the surface must be completely removed.</li><li>3. The proper pH of the material must be less than 9, and the percentage of moisture content must be less than 6%.</li><li>4. The gaps and grooves on the surface must be filled with exterior water-based putty, and surface adjustment should be made before coating.</li></ol>
Coating Method	<ol style="list-style-type: none"><li>1. Primer<ol style="list-style-type: none"><li>① After surface treatment, dilute the water-based permeable sealer DNX-4001 with water up to 100%, and apply once at a dry film thickness of 15μm with a roller or brush.</li><li>② For areas where the absorption of the surface is severe, apply once more coating.</li></ol></li><li>2. Top Coat<ol style="list-style-type: none"><li>① After at least 3 hours at 20℃ following undercoating, apply this paint twice to get a dry film thickness of 60μm with a brush, roller or spray.</li><li>② At this time, apply by diluting with water up to 20%.</li><li>③ After 2 coats, the re-coating interval is at least 3 hours after the first top coating at 20℃.</li></ol></li></ol>