



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-31-499-5390

FAX 82-31-499-6867

Report No : TAK-2019-192961

Receipt Date : 2019.11.11.

Representative : Jin Myeong ho, Kim Yong Kee

Test Completion Date : 2020.03.05.

Company name : NOROO Paint & Coatings Co., Ltd.

Address : (Bakdal-dong)351, Bakdal-ro, Manan-gu, Anyang-si, Gyeonggi-do, Korea

Sample name : ECO-CRETE 200 SL

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Impact Resistance	-	-	No defects	KS F 4937 : 2009
Adhesive Strength	N/mm ²	-	2.9	KS F 4937 : 2009
Wheel load resistance - Surface state	-	-	No defects	KS F 4937 : 2009
Wheel load resistance - decreased depth of thickness	mm	-	0.3	KS F 4937 : 2009
Watertightness	-	-	No defects	KS F 4937 : 2009
TVOC emission	mg/m ² · h	-	0.177	KS F 4937 : 2009
Toluene emission	mg/m ² · h	-	0.005 below	KS F 4937 : 2009
Formaldehyde emission	mg/m ² · h	-	0.005 below	KS F 4937 : 2009

* This is a test specimens provided by the client after completing the production and curing.

* Emission Test Condition

1. Test period : 7 days

2. Load factor : 0.4 m² / m³

3. Sample : Paint (Applied area: 63 mm x 63 mm x 2 ea, Client provided sample)

4. MDL : TVOC - 0.020 mg/m² · h, HCHO - 0.005 mg/m² · hToluene - 0.005 mg/m² · h

- Usage of Report : QUALITY CONTROL

- Next Page -

Park Sanghyo

Prepared by Park Sanghyo

Tel : 032-570-9643

Jong-Kuk Kwon

Reviewed by Jong-Kuk Kwon

Tel : 1577-0091(ARS ①→④)

2020.03.05

Korea Testing & Research Institute

President



QR Code for forgery

Registered copy date : Mar.16.2020

Page : 1 of 2

전자문서본은 시험결과에 대한 참고용입니다.

전자문서본(Electronic Copy)



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-31-499-5390

FAX 82-31-499-6867

Report No : TAK-2019-192961

Receipt Date : 2019.11.11.

Representative : Jin Myeong ho, Kim Yong Kee

Test Completion Date : 2020.03.05.

Company name : NOROO Paint & Coatings Co., Ltd.

Address : (Bakdal-dong)351, Bakdal-ro, Manan-gu, Anyang-si, Gyeonggi-do, Korea

Sample name : ECO-CRETE 200 SL

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
-----------	------	--------	--------	-------------

- Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Park Sanghyo

Prepared by Park Sanghyo

Tel : 032-570-9643

Jong-Kuk Kwon

Reviewed by Jong-Kuk Kwon

Tel : 1577-0091(ARS ①→④)

2020.03.05

Korea Testing & Research Institute

President



QR Code for forgery

Registered copy date : Mar.16.2020

Page : 2 of 2

전자문서본은 시험결과에 대한 참고용입니다.

전자문서본(Electronic Copy)