



TEST REPORT

1. NO : CT20-007948E

2. Client

○ Name : Noroo Paint & Coatings Co., Ltd

○ Address : Bakdal-ro 351, Manan-gu, Anyang-si, Gyeonggi-do

3. Date of Test : 2020.01.15 ~ 2020.02.13

4. Use of Report :

5. Test Sample : ECO-CRETE

6. Test Method

(1) JIS Z 2801:2012

7. Test Results

1) ECO-CRETE

Test Item(s)	Unit	Test Method	Test Results	Remark
Anti-bacterial Test(Klebsiella pneumoniae)-antibacterial activity	Log value	(1)	5.5	(35.0 ± 0.1) °C (92.9 ± 0.5) % R.H.
Anti-bacterial Test(MRSA)-antibacterial activity	Log value	(1)	5.6	(35.0 ± 0.1) °C (92.9 ± 0.5) % R.H.

※ Test bacteria : Klebsiella pneumoniae ATCC 4352, MRSA(Staphylococcus aureus subsp. aureus) ATCC 33591

※ Sample : 5 cm × 5 cm, Blank : Stomacher film : 5 cm × 5 cm

※ Covering film : 16 cm²

※ Incubation time : 24 hours

----- End of Report -----


Affirmation	Tested By Name : Lee, jeoung yun	Technical Manager Name : Park Dong Hyup
Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. The results of using only a portion of this report cannot be guaranteed. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr).		

2020.02.13

Korea Conformity Laboratories

President Yoon, Kap Seok *Yoon, Kap Seok*

Result Inquiry : 628, Sorae-ro, Namdong-gu, Incheon, 21594, Korea (82-32-460-5163)





TEST REPORT

1. NO : CT20-007949E

2. Client

○ Name : Noroo Paint & Coatings Co., Ltd

○ Address : Bakdal-ro 351, Manan-gu, Anyang-si, Gyeonggi-do

3. Date of Test : 2020.01.15 ~ 2020.02.13

4. Use of Report :

5. Test Sample : ECO-CRETE

6. Test Method

(1) JIS Z 2801:2012

7. Test Results

1) ECO-CRETE

Test Item(s)	Unit	Test Method	Test Results	Remark
Anti-bacterial Test(Escherichia coli)-antibacterial activity	Log value	(1)	5.8	(35.0 ± 0.1) °C (92.9 ± 0.5) % R.H.
Anti-bacterial Test(Pseudomonas aeruginosa)-antibacterial activity	Log value	(1)	5.9	(35.0 ± 0.1) °C (92.9 ± 0.5) % R.H.
Anti-bacterial Test(Staphylococcus aureus)-antibacterial activity	Log value	(1)	5.7	(35.0 ± 0.1) °C (92.9 ± 0.5) % R.H.

* Test bacteria : Escherichia coli ATCC 8739, Pseudomonas aeruginosa ATCC 15442, Staphylococcus aureus ATCC 6538P

* Sample : 5 cm × 5 cm, Blank : Stomacher film : 5 cm × 5 cm

* Covering film : 16 cm²

* Incubation time : 24 hours

----- End of Report -----

Affirmation	Tested By	이정운	Technical Manager	
	Name : Lee, jeoung yun		Name : Park Dong Hyup	

Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. The results of using only a portion of this report cannot be guaranteed. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr).

2020.02.13

Korea Conformity Laboratories

President Yoon, Kap Seok

Result Inquiry : 628, Sorae-ro, Namdong-gu, Incheon, 21594, Korea (82-32-460-5163)

