

순&수 우드플로어

※ 본 제품은 실내공기질관리법에 따른 다중이용시설 및 100(이상)~500(미만) 세대 공동주택의 실내에 사용 가능한 제품입니다

본 도료는 특수 아크릭 수지와 우레탄 수지를 적용하여 도막이 강하고 질기며 내구성, 내스크래치성 및 내수성이 우수한 바니쉬 제품입니다. 특히, 목재 부착성이 우수하여 내부 목재 마감면뿐 아니라 체육관 바닥면에도 도장이 가능한 고기능성 수성 도료입니다.

용 도	실내 체육관 목재 바닥, 건축물의 내부 목재 및 가구
-----	-------------------------------

제 품 특 성

페인트타입	아크릭/우레탄 수지			
건 조 시 간	구 분	5℃	20℃	30℃
	고화건조	3~4시간	2~3시간	1~2시간
	재도장가능시간(최소)		2시간	
희 석 제	상수도물(희석율:최대5%, 부피비)		도장방법	붓, 롤러, 스프레이도장
비 중	약 1.0±0.1		고형분용적비	약 32 %
이론도포량	9.9 m ² /l/1회		건조도막두께	30µm~40µm (2회도장 추천)
재도장간격	20℃, 충분한 환기 최소 2시간 이상		색 상	투명
광택	유광		포장 단위	4L, 18L
보관 및 저장	12개월(통풍이 잘되는 건냉암소, 상온 5℃~30℃, 습도 80%이하)			

제 품 특 징 (물성 DATA)

미려한 외관	목재면을 매끈하게 하여 미려한 외관을 부여합니다.
도막 물성	내스크래치성, 내수성, 내구성이 우수합니다. (실온에서 5일 이상 건조후에 도막물성 발취)
	※ 도막물성이 발휘되기전에 사용할 경우 광택 저하 및 스크래치가 발생할 수 있습니다.
환경성	실내 도장시 냄새가 거의 없습니다.

사 용 방 법

표면처리	1. 소지표면의 거친부분은 #180-220의 샌드페이퍼로 곁을 따라 연마하여 평활하게 하십시오. 2. 소지표면에 기름기나 오염물 및 연마분은 깨끗이 제거하고 완전히 건조시키십시오. 3. 젖은 나무는 완전 건조시키고 곰팡이는 완전 제거후에 도장하십시오.
도장방법	1. 하도 1) 지정하도인 그린라카 샌딩실러를 1회 도장합니다 2. 상도 1) 순&수 우드플로어를 1회 도장하고 2시간 건조 후에 재도장합니다. 1회 도장시 지나치게 두꺼운 도장은 피하십시오. (기포 발생 우려 있음) 2) 재도장시간이 짧으면 도장후 건조중에 기포가 발생할 수 있습니다. 3) 도장 시 소재, 제품, 기온이 10℃를 이하일 경우 도막이 약하거나 갈라지는 등의 문제가 발생하여 정상적인 물성을 발휘하지 못하므로 도장작업을 피하십시오.

NOROO 노루페인트

SOON&SOO WOOD FLOOR

※ This product can be used inside multi-use facilities and 100-500 unit apartment houses under The Indoor Air Quality Control Act.

SOON&SOO WOOD FLOOR is a waterbased urethane coating for wood finish composed of special acrylic resin and urethane resin. It makes the coated film strong and durable and has excellent durability, scratch resistance and water resistance. In particular, it is a high-performance waterbased paint that can be applied to floors of indoor gym as well as indoor wood finish due to its excellent adhesion to wood.

Usage	Indoor gym floor, wood and furniture
-------	--------------------------------------

Specification

Paint type	Acrylic / Urethane resin			
Drying time	Category	5℃	20℃	30℃
	Dry-hard	3~4 hours	2~3 hours	1~2 hours
	Time required for re-coating (min.)		2 hours	
Thinner	Tap water(dilution rate: less than 5%, volume ratio)		Coating Method	Brush, roller, spray coating
Specific gravity	Approx. 1.0±0.1		Solid volume ratio	Approx. 32 %
Theoretical Coverage	9.9 m ² /l/1time		Thickness of dried film	30μm~40μm (2 coats recommended)
Re-coating interval	20℃, sufficient ventilation for a minimum of 2 hours		Color	Transparent
Gloss	Glossy		Packaging unit	18Lt, 4Lt
Storage and preservation	12 months (well-ventilated dry, cold and dark location, room temperature 5℃~30℃, humidity less than 80%)			

Product Properties (Physical Property Data)

Beautiful appearance	Imparts a beautiful appearance by smoothing the timber surface.
Film property	Scratch resistance, water resistance and durability are excellent. (Sufficient performance is achieved after drying for more than 5 days at room temperature) ※ If used before the properties of the coating film are exhibited, gloss deterioration and scratches may occur.
Environmental impact	It has little odor upon interior painting.

How to Use

Surface treatment	1. Sand irregular surfaces using #180-220 sandpaper. 2. Completely clean grease or contaminants and abrasion powder on the surface of the substrate and thoroughly dry it. 3. Thoroughly dry the wet wood and completely remove the mold before coating.
Coating Method	1. Primer 1) Apply the designated primer, GREEN LACQUER SANDING SEALER 1 coat. 2. Topcoat 1) Apply the first coat of SOON&SOO Wood Floor and let it dry for 2 hours. Then apply the second coat. Do not try to achieve thick film in a single coat. Bubbles may occur. 2) If the overcoat time is short, air bubbles may occur during drying. 3) Do not use when the substrate, product or ambient temperature is below 10℃.

NOROO 노루페인트