

NR CRYSTAL(W) FAST



Solvent Free Clear Epoxy

This paint is a 2K non-solvent type epoxy clear paint composed mainly of non-solvent-based epoxy resin and modified amine resin. It is excellent in the hardness of dry film, adhesion, durability, chemical resistance and dust proofness. It has excellent smoothness and can form a beautiful appearance after painting. It is more effective if an interior design is applied before applying this paint.

Usage

Clear epoxy for concrete surfaces

Specification

Paint type	Modified epoxy / Modified amine (2-Component)			
Drying time	Category	5℃	20℃	30℃
	Set-to-touch	5 hours	2.5 hours	3 hours
	Dry-through	18 hours	8 hours	10 hours
	Pot life	20 minutes	10 minutes	5 minutes
	Above pot life and follow-up coating time have been measured under laboratory conditions and may vary depending on the construction site. The film that has passed the maximum follow-up coating time may have adhesion failure. Please apply after checking the proper surface treatment and adhesion.			
Thinner	Not Applicable	Dilution ratio	▷ No dilution ▷ In case of high viscosity in the winter season, dilute within the volume ratio 1%	
Specific gravity	Approx. 1.09			
Theoretical Coverage	100 sq. ft./gal.	Solid volume ratio	100%	
Color	Clear (Compounds)	Thickness of dried film	16mils	
Mixing ratio	Base(A)/hardener(B)=2/1 (Volume ratio)	Gloss	Glossy	
Shelf life	12 months	Packaging unit	Available as customized	

How to Use

Surface treatment	<ol style="list-style-type: none">1. Cure concrete for at least 28 days at a temperature of 21°C and a relative humidity of 50%.2. Completely remove the oil, moisture, sand, dust, laitance and other foreign matter from the surface and maintain surface smoothness.
Coating Conditions	<ol style="list-style-type: none">1. Atmosphere Temperature: 5~35°C, Surface Temperature: 40°C or below, Relative Humidity: 80% or less, Moisture content in the concrete: 6% or less2. Due to the nature of epoxy lining transparent paint, a color difference may be shown over time if the coating surface is a bright color.3. The degree of occurrence of yellowing varies depending on the long-term exposure to sunlight or the use time of indoor lighting, etc.4. The use of a thinner more than the recommended amount causes a further delay in drying.5. Pot life will be shorten when mixing mass volumes of A+B as it generates heat reaction. So, we recommend you follow the below procedures when applying bucket packing of it. (15 gallon) a. Stir Part A and Part B separately before mixing together. b. Apply on the surface to be coated as soon as PART A + PART B are mixed uniformly together because of short pot life.
Coating Method	<ol style="list-style-type: none">1. Reinforce cracks, crevices, and joints between walls and floors with an epoxy putty after primer.2. Apply smoothly using sawtooth scraper, rubber scraper, pitchfork, square towel, etc.3. Care should be taken since problems may occur such as cratering upon thin coating. (2mm or less - 1 time) <p>Appropriate construction specifications</p> <p>▷ Primer : Epoxy primer</p> <p>▷ Mid coat : Epoxy/polyurea basecoat</p> <p>▷ Top coat : Urethane/polyaspartic(optional)</p>