NRP-CFC-1953

Silicone confomal coating

NRP-CFC-1953 is a one-component humidity-curable coating agent that consists of an oil-based silicone resin. It serves to maintain long-term reliability by protecting PCA (Printed Circuit Assembly) from high humidity and harsh environment.

| Usage | Protective coating for PCA (Printed Circuit Assemble) | | |
|---|---|--------------------|---|
| Specification | | | |
| Coating type | One-component silicone | | |
| Product features | 1. It features varying workability. | | |
| | 2. It dries quickly at room temperature. | | |
| | 3. It features outstanding electrical and physical properties. | | |
| | 4. It protects the substrate from harsh environment. | | |
| | 5. It features outstanding durability. | | |
| | 6. It has various product lines ranging from 350 to 5,300 cps. | | |
| Thinner | Designated thinner | Pot time (25 °C) | One-componet |
| Exterior | Transparent liquid | | |
| Viscosity | 350 - 5,300 | Curing conditions | Air-drying or hot air drying |
| Specific gravity | 0.97 ± 0.05 | UL-certified | Not certified |
| Tack-free time (room temperature) | 5 - 12 min. | Storage conditions | Store in a shaded indoor space with sufficient ventilation. |
| Mixing ratio | One-component | Shelf life | 6 months from the manufacturing date (when stored at room temperature) |
| Product Properties (Physical Property Data) | | | |
| Durometer | 15 (share A type) | | |
| Dielectric strength | 18 - 20 (kV/mm) | | |
| How to Use | | | |
| How to Use | | | |
| | 2. Dry according to the designated curing conditions. | | |
| Note | 1. Instructions above may vary depending on the type of substrate and the painting line conditions. | | |
| | 2. This product is a one-component product that can be used immediately without mixing the base and the hardener. | | |
| | 3. Please refer to the MSDS when handling the product. | | |
| | 4. Its shelf life is 6 months at room temperature. | | |
| The data shown above were obtained under the laboratory conditions, and the product properties may vary depending on work method and circumstances. Please refer to | | | |

▶ The data shown above were obtained under the laboratory conditions, and the product properties may vary depending on work method and circumstances. Please refer to the property data listed above only as reference.

NOROO 노루페인트