DUM-5500



Insulation resin for Casting

DUM-5500 is a product for casting used in the urethane curing system and features outstanding elasticity, water resistance, and drying performance. This product maintains elasticity even at low temperature which makes it suitable for components requiring low noise or water resistance.

Usage	For casting PCB and electric components		
Specification			
Type of varnish	Two-component urethane resin		
Product Features	 It acquired flammability UL94 V-0 certification. It features outstanding water resistance. It features outstanding electrical properties. It features outstanding thermal shock resistance. It can be cured at low temperature as well as at room temperature. 		
Thinner	None	Pot time (25 °C) (A + B)	Within 30 min.
Exterior	All colors		
Viscosity	18 - 22 POISE	Curing conditions	25 °C x 24 hours or more / 50 - 60 °C x 2 - 4 hours
Specific gravity	1.42 ± 0.02	UL-certified	Flame retardant level V-0 (UL-94, E209384)
Set-to-touch drying (25 °C)	Within 3 hours	Storage conditions	Store in a shaded indoor space with sufficient ventilation.
Mixing ratio	A : B = 100 : 20 (Weight)	Shelf life	6 months from the manufacturing date (when storage conditions are met)
Product Properties (Physical Property Data)			
Breakdown voltage	Above 10 KV/mm		
Volume resistivity	At least $1.0 \times 10^{13}~\Omega cm$		
Hardness	75 - 85 (SHORE-A)		
How to Use			
	Mix evenly after adding the substances according to the designated mixing ratio.		
	2. Defoam with vacuum to eliminate air pockets.		
How to Use	3. Inject well-mixed epoxy to the substrate.		
	4. Dry according to the designated curing conditions.		
	1. Instructions above may vary depending on the type of substrate and the painting line conditions.		
	2. Liquid B is weak against moisture, so use the product quickly after opening it.		
Caution	3. If the humidity is high, there is a possibility of exterior defect due to foaming during the curing.		
	So use the product in an indoor space where humidity can be controlled.		
	4. Please refer to the MSDS when handling the product.		

[▶] The data shown above were obtained under the laboratory conditions, and the product properties may vary depending on work method and circumstances. Please refer to the property data listed above only as reference.

