



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-31-499-5390

FAX 82-31-499-6867

Report No : TAK-2019-192917

Receipt Date : 2019.11.11.

Representative : Jin Myeong ho, Kim Yong Kee

Test Completion Date : 2020.01.16.

Company name : NOROO Paint & Coatings Co., Ltd.

Address : (Bakdal-dong)351, Bakdal-ro, Manan-gu, Anyang-si, Gyeonggi-do, Korea

Sample name : DHDC-3650TL

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Condition in Container(Base)	-	-	No Detects	KS M 5000 : 2014
Viscosity(Base)	K.U	-	121	KS M 5000 : 2014
Specific Gravity(Base)	-	-	1.83	KS M ISO 2811-1 : 2016
Fineness of Grind(Base)	μm	-	30	KS M ISO 1524 : 2013
Appearance for Dried Film	-	-	No Detects	KS M 5000 : 2014
Nonvolatile Content((105 ± 2) °C, 3 h)	%	-	89.4	KS M ISO 3251 : 2011
Drying Time(Dry Hard)	h	-	10	KS M 5000 : 2014

- Mixing Ratio = Base : Hardener = 5 : 1 (by mass)

- Usage of Report : QUALITY CONTROL

- Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Kang Myeongu

Prepared by Kang Myeongu

Tel : 02-2092-3711

Huh Namjung

Reviewed by Huh Namjung

Tel : 1577-0091(ARS ①→④)

2020.01.16

Korea Testing & Research Institute

President



QR Code for forgery

Registered copy date : Feb.10.2020

Page : 1 of 1

전자문서본은 시험결과에 대한 참고용입니다.

전자문서본(Electronic Copy)