



TEST REPORT

1. NO : CT22-003327E
2. Client
 - Name : NOROO Paint & Coatings Co.,Ltd.
 - Address : 129, Gongdandong-gil, Chilseo-myeon, Haman-gun, Gyeongsangnam-do, Republic of Korea
3. Date of Test : 2022.01.07 ~ 2022.05.18
4. Use of Report : Quality control
5. Test Sample : CLEANPOXY MORTAR DHDC-6500
6. Test Method
 - (1) KS F 4937:2019
 - (2) Client's Requirement [KS F 4937:2019]

Affirmation	Tested By		Technical Manager	
	Name : HONG SUNG ROG		Name : Shin, Hong Chul	


This report is not accredited by KOLAS and KS Q ISO/IEC 17025.
 Our report apply only to the standards or procedures identified and to the sample(s) tested unless otherwise specified. The test results are not indicative of representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products. The results of using only a portion of this report cannot be guaranteed. The authenticity of this test report can be checked on KCL website(www.kcl.re.kr).

2022.05.18

Korea Conformity Laboratories

President Jo, Yung Tae

Result Inquiry : 73, Yangcheong 3-gil, Ochang-eup, Cheongwon-Gu, Cheongju-Si, Chungbuk, Korea (82-43-210-8948)



TEST REPORT

No : CT22-003327E

7. Test Results

1) CLEANPOXY MORTAR DHDC-6500

Test Item(s)	Unit	Test Method	Test Results	Remark	Loc.
Impact resistance performance	-	(1)	Pass	(20±2) °C, (65±5) % R.H.	A
Bond strength	N/mm ²	(1)	3.1		
Wheel load resistance performance(Surface Condition) - (300 kg, 80 000 times)	-	(1)	Pass		
Wheel load resistance performance(Thickness reduction) - (300 kg, 80 000 times)	mm	(1)	0.4		
Water Permeability Resistance performance	-	(1)	Pass		
Total Volatile Organic Compounds (TVOC)	mg/(m ² ·h)	(2)	0.018	-	B
Toluene	mg/(m ² ·h)	(2)	N/D (MDL 0.000 5)		
Formaldehyde	mg/(m ² ·h)	(2)	N/D (MDL 0.000 5)		

※ This is the result of the test with the test specimen provided by the client.

※ The above is the result of test specimen provided by the applicant

※ Location

A : 73, Yangcheong 3-gil, Ochang-eup, Cheongwon-Gu, Cheongju-Si, Chungbuk, Korea

B : #805, I Valley, 149, Gongdan-ro, Gunpo-si, Gyeonggi-do, Korea

----- End of Report -----

