



## TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-31-499-5390

FAX 82-31-499-6867

Report No : TAK-2019-192966

Receipt Date : 2019.11.11.

Representative : Jin Myeong ho, Kim Yong Kee

Test Completion Date : 2020.02.24.

Company name : NOROO Paint &amp; Coatings Co., Ltd.

Address : (Bakdal-dong)351, Bakdal-ro, Manan-gu, Anyang-si, Gyeonggi-do, Korea

Sample name : ECO-CRETE 200 SL

## Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Hardness(Hs D)	-	-	84	KS M 6518 : 2018[*1]
Compressive Strength	N/mm <sup>2</sup>	-	60.4	KS F 4042 : 2012(Apply correspondingly)
Flexural Strength	N/mm <sup>2</sup>	-	18.4	KS F 4042 : 2012(Apply correspondingly)

\* Test specimen : By client

[\*1]At the request of the Client, Test Method of KS M 6518 : 2018 is applied.

- Usage of Report : QUALITY CONTROL

- Note :
1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
  2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
  3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

*Park Sanghyo*

Prepared by Park Sanghyo

Tel : 032-570-9643

*Jong-Kuk Kwon*

Reviewed by Jong-Kuk Kwon

Tel : 1577-0091(ARS ①→④)

2020.02.24

Korea Testing &amp; Research Institute

President



QR Code for forgery

Registered copy date : Mar.16.2020

Page : 1 of 1

전자문서본은 시험결과에 대한 참고용입니다.

전자문서본(Electronic Copy)