



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-31-499-5390

FAX 82-31-499-6867

Report No : TAK-2022-169185

Receipt Date : 2022.12.13.

Representative : Jin Myeong ho, Kim Yong Kee

Test Completion Date : 2023.01.30.

Company name : NOROO Paint & Coatings Co., Ltd.

Address : (Bakdal-dong)351, Bakdal-ro, Manan-gu, Anyang-si, Gyeonggi-do, Korea

Sample name : NR CRYSTAL(V)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Durometer Hardness(Type D)	-	-	80	ASTM D2240-15e1
Tensile Strength(**)	MPa	-	58.2	ASTM D638-22
Elongation at Break(**)	%	-	2.4	ASTM D638-22
Compressive Strength(***)	MPa	-	127	ASTM D695-15
Flexural Strength(****)	MPa	-	99.5	ASTM D790-17
Izod Impact Strength	J/m	-	27.9	ASTM D256-10(2018)
Water Absorption(24 h Immersion)	%	-	0.11	ASTM D570-22
Taber Abrasion Test(Weight Loss)(*****)	mg	-	28	ASTM D4060-19
Adhesion Strength(*)	MPa	-	2	KS M ISO 4624 : 2016

* Surface: Iron plate, Adhesive: 2-component epoxy, Test speed: below 1 MPa/s

Fracture Characteristics: Cohesive fractures by the coat(B)

Test equipment: PosiTest AT (Defelsko- USA)

* This is the result of the test with the specimen provided by the client.

** Specimen : Type I, Speed of testing : 5 mm/min

*** Specimen : Prism

**** Speed of testing : 1.8 mm/min, Support span : 70 mm

***** Wheels : CS-17, Weight : 1 000 g, Cycles : 1 000

- Usage of Report : QUALITY CONTROL

- Next Page -

Park Seungphyo

Prepared by Park Seungphyo

Tel : 02-2092-3696

Choi Byung Il

Reviewed by Choi Byung Il

Tel : 1577-0091(ARS ①→④)

2023.01.30

Korea Testing & Research Institute

President



QR Code for forgery



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-31-499-5390

FAX 82-31-499-6867

Report No : TAK-2022-169185

Receipt Date : 2022.12.13.

Representative : Jin Myeong ho, Kim Yong Kee

Test Completion Date : 2023.01.30.

Company name : NOROO Paint & Coatings Co., Ltd.

Address : (Bakdal-dong)351, Bakdal-ro, Manan-gu, Anyang-si, Gyeonggi-do, Korea

Sample name : NR CRYSTAL(V)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
-----------	------	--------	--------	-------------

- Note : 1. The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
2. This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
3. This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Park Seungphyo

Prepared by Park Seungphyo

Tel : 02-2092-3696

Choi Byung Il

Reviewed by Choi Byung Il

Tel : 1577-0091(ARS ①→④)

2023.01.30

Korea Testing & Research Institute

President



QR Code for forgery