



TEST REPORT

98, Gyoyukwon-ro, Gwacheon-si, Gyeonggi-do, 13810, Korea

TEL 82-31-499-5390

FAX 82-31-499-6867

Report No : TAK-2022-038744

Receipt Date : 2022.03.15.

Representative : Jin Myeong ho, Kim Yong Kee

Test Completion Date : 2022.04.06.

Company name : NOROO Paint & Coatings Co., Ltd.

Address : (Bakdal-dong)351, Bakdal-ro, Manan-gu, Anyang-si, Gyeonggi-do, Korea

Sample name : Water-based Elastic Waterproofing Paint (Intermediate)

Test Results

TEST ITEM	UNIT	SAMPLE	RESULT	TEST METHOD
Tensile strength	N/mm ²	-	1.6	KS F 3211 : 2015
Elongation at break	%	-	238	KS F 3211 : 2015
Adhesion Strength Test(thin coating)(**)	N/cm ²	-	50.3	KS M 6010 : 2014(Application)

** This is the result of testing according to the three types of KS M 6010 : 2014.

- Usage of Report : QUALITY CONTROL

- Note :
- The test results of this test report are only limited in to the samples and sample names provided by the client and do not guarantee the quality of all products of the client. You Can check website (www.ktr.or.kr) or QR code to verify the authenticity of the certificate.
 - This test report shall be used only within the purpose of its defined usage and shall not be used for public relation, advertisement and lawsuit.
 - This test report is only valid when printed on KTR original report paper with hologram and when re-issued by KTR. The copy and the electronic file of the test report are only for reference.

Kang Myeongu

Prepared by Kang Myeongu
Tel : 02-2092-3711

Jung Bong Kue

Reviewed by Jung Bong Kue
Tel : 1577-0091(ARS ①→④)

2022.04.06

Korea Testing & Research Institute

President



QR Code for forgery