

CLEANTHANE 3000K

Elastic urethane top coat for waterproofing



This paint is a two-component elastic urethane top coat based on urethane resin (non-yellowing). Unlike ordinary urethane paints, it is highly flexible and suitable as a top material for elastic waterproofing materials. In particular, it is excellent in weather resistance, hiding power, adhesion and abrasion resistance and is a top material for the exposed type waterproofing material.

Usage

Exposure type waterproofing material top coat

Specification

Paint type	Polyurethane resin (Two-Component)			
Drying time	Category	5℃	20℃	30℃
	Set-to-touch	1 hour	30 minutes	20 minutes
	Dry-through	18 hours	12 hours	8 hours
	Over-coat (Min.)	18 hours	12 hours	8 hours
	Over-coat (Max.)	5 days	3 days	2 days
	Pot life	6 hours	4 hours	2 hours
	Above pot life and follow-up coating time have been measured under laboratory conditions and may vary depending on the construction site.			
Thinner	DR-700, DR-700L, DR-790	Dilution ratio	▷ Dilution rate: up to 10%, volume ratio	
Specific gravity	1.13 (Based on green color)			
Theoretical Coverage	0.11 kg/m²	Solid volume ratio	43±3 % (Based on green color)	
Color	Green, other ordered colors	Thickness of dried film	40 μm	
Mixing ratio	Base(A)/Hardener(B)=8/1 (Weight ratio)	Gloss	Glossy (semi-gloss, matte made to order)	
Shelf life	12 months	Packaging unit	16 kg [Base(14.22 kg), Hardener(1.78 kg)]	
Flash point	27 °C			

How to Use

Surface treatment	<ol style="list-style-type: none">1. Cure concrete for at least 28 days at a temperature of 21°C and a relative humidity of 50%.2. Completely remove the oil, moisture, sand, dust, laitance and other foreign matter from the surface and maintain surface smoothness.3. For high-strength concrete (260kg/m² or higher), blasting treatment should be carried out.
Coating Conditions	<ol style="list-style-type: none">1. Atmosphere Temperature: 5~35°C, Surface Temperature: 40°C or below, Relative Humidity: 80% or less.
Coating Method	<ol style="list-style-type: none">1. Reinforce cracks, crevices, and joints between walls and floors with the NEW-THANSUNG SEAL(N).2. Apply smoothly on the undercoated surface using sawtooth scraper, rubber scraper, pitchfork, roller, etc. <p>Appropriate construction specifications</p> <ul style="list-style-type: none">▷ Primer : CLEANTHANE 1000▷ Intermediate coating : ECO-CLEANTHANE 2100▷ Top coat : CLEANTHANE 3000K