

BEAUTITEX (EXTREME FLAT)

Water-based paint for ceilings

This paint is a water-based interior paint that is made mainly of acrylic emulsion resin and pigment excellent in hiding power. It is designed to be suitable for painting the ceilings of a building. In particular, it is an interior water-based product that can minimize uneven brightness caused by painting tools due to its low gloss.

Usage

Finish coating for interior ceilings of alkaline material buildings

Specification

Paint type	Acrylic emulsion water-based interior / Top coat			
Drying time	Category	10°C	20°C	30°C
	Set-to-touch	1 hour	30 minutes	20 minutes
	Dry-hard	2 hours	1 hour	1 hour
	Time required for re-coating (min.)	6 hours	3 hours	2 hours
Thinner	Tap water(dilution rate: up to 20%, volume ratio)	Coating Method	Brush, roller, spray coating	
Specific gravity	Approx. 1.4(based on white color)	Solid volume ratio	Approx. 31%(based on white color)	
Theoretical Coverage	5~6m ² /ℓ/2times	Thickness of dried film	60μm (2coats recommended)	
Re-coating interval	20°C, sufficient ventilation for a minimum of 3 hours	Color	White, other colors	
Gloss	Matte			
Storage and preservation	12 months (Dry, cool, and dark place with good ventilation, room temperature 5°C~30°C, humidity less than 80%)			

Product Properties (Physical Property Data)

Beautiful appearance	The gloss on the coated surface is very low.
Excellent workability	There is almost no uneven brightness caused by the painting tool.
Excellent hiding power	Efficient coating can be carried out due to its excellent hiding power and workability

How to Use

Surface treatment	<ol style="list-style-type: none">1. The material should be sufficiently cured (cured more than 30 days at 20°C)2. Laitance, dust, oil and other contaminants on the surface must be completely removed.3. The proper pH of the material must be less than 9, and the percentage of moisture content must be less than 6%.4. The gaps and grooves on the surface must be filled with exterior water-based putty, and surface adjustment should be made before coating.
Coating Method	<ol style="list-style-type: none">1. Primer<ol style="list-style-type: none">① After surface treatment, dilute the water-based permeable sealer DNX-4001 with water up to 100%, and apply once at a dry film thickness of 15μm with a roller or brush.② For areas where the absorption of the surface is severe, apply once more coating.2. Top Coat<ol style="list-style-type: none">① After at least 3 hours at 20°C following undercoating, apply this paint twice to get a dry film thickness of 60μm with a brush, roller or spray.② At this time, apply by diluting with water up to 20%.③ After 2 coats, the re-coating interval is at least 3 hours after the first top coating at 20°C.